


5 Foot x 10 Foot Rectangular Plastic Tree Grate



TSB12060FE

| PRODUCT AND MATERIAL TEST DATA | | | |
|--------------------------------|-----------|------------|----------------|
| RESIN PROPERTIES | ASTM TEST | UNITS | TYPICAL VALUES |
| DENSITY | D-1505 | G / CC | 0.957 |
| MELT INDEX | D-1238 | G / 10 MIN | 7 |
| MOLDED PROPERTIES | ASTM TEST | UNITS | TYPICAL VALUES |
| MODULUS | D-638 | PSI | 166 000 |
| TENSILE AT YIELD | D-638 | PSI | 430 |
| ELONGATION AT BREAK | D-638 | % | 1 400 |
| FLEXURAL MODULUS | D-790 | PSI | 194 000 |

- NOTES:
1. INSTALLATION TO BE COMPLETED IN ACCORDANCE WITH MANUFACTURER'S SPECIFICATIONS.
 2. DO NOT SCALE DRAWING.
 3. THIS DRAWING IS INTENDED FOR USE BY ARCHITECTS, ENGINEERS, CONTRACTORS, CONSULTANTS AND DESIGN PROFESSIONALS FOR PLANNING PURPOSES ONLY. THIS DRAWING MAY NOT BE USED FOR CONSTRUCTION.
 4. ALL INFORMATION CONTAINED HEREIN WAS CURRENT AT THE TIME OF DEVELOPMENT BUT MUST BE REVIEWED AND APPROVED BY THE PRODUCT MANUFACTURER TO BE CONSIDERED ACCURATE.